












Technical information (04/2021)

GRAVIHEL ALKYD PRIMER 20 GREY

- One-component priming coat based on an alkyd binder, used as anti-corrosion protection of steel surfaces.
- It is distinguished by extremely quick drying (approx. 20 minutes), it is also suitable for application by immersion.
- Brush application is only suitable for smaller surfaces, as more coats are required to achieve the recommended thickness of dry film compared to spraying application.
- With a film thickness of up to 25µm, it enables subsequent welding without any effect on the quality of the weld.
- Combined with an adequate top coating, it is suitable for exposure in a countryside, city or mild industrial atmosphere.
- VOC compliant

SUBSTRATE PREPARATION	
	 P220 – P280
	 GRAVIHEL Antisilicone cleaner

Typ of product:	Alkyd
Appearance	MATT
Delivery viscosity:	Thixotropic
DIN 53211 Φ4 / 20°C	
Density of component A:	1,283 – 1,415 kg/l
Solid content:	By volume: 34%
	By weight: 70%
VOC:	2004/42/II B(c)(540)530
	EU limit value VOC for this type of product (category II B (c)) in the form, which is ready for application is 540 g/l. VOC of this product, prepared for use is 530 g/l
	IT IS ALSO USED TO RENOVATE INDUSTRIAL AND COMMERCIAL VEHICLES
Theoretical yield:	7 - 8 m ² /lit.
Temperature resistance (dry temperature)	Short-term: up to 140 °C Long-term: up to 120 °C
Processing temperature:	+5°C till max. +40°C, max.Humidity 85%
Color shades:	GREY

	Viscosity (RFU): DIN 53211 Φ4 / 20°C	32 - 35 sec. GRAVIHEL 1K THINNER (15%)																		
	Application with spray gun:	1,5 – 1,7 mm 2 – 3 bar																		
	Number of layers: Film thickness:	2 40 - 50 μm																		
	Flash-off:	5 - 10 min. /20°C between coats																		
	Drying time:	<table border="1"> <thead> <tr> <th>Object temperature</th> <th>at 20°C</th> <th>at 60°C</th> </tr> </thead> <tbody> <tr> <td>Powder dry:</td> <td>7 min.</td> <td>-</td> </tr> <tr> <td>Dry to touch:</td> <td>40 min.</td> <td>-</td> </tr> <tr> <td>Dry to assembly:</td> <td>2 h</td> <td>30 min.</td> </tr> <tr> <td>Dry for sanding:</td> <td>2 h</td> <td>30 min.</td> </tr> <tr> <td>Top coat:</td> <td>2 h</td> <td>30 min.</td> </tr> </tbody> </table>	Object temperature	at 20°C	at 60°C	Powder dry:	7 min.	-	Dry to touch:	40 min.	-	Dry to assembly:	2 h	30 min.	Dry for sanding:	2 h	30 min.	Top coat:	2 h	30 min.
Object temperature	at 20°C	at 60°C																		
Powder dry:	7 min.	-																		
Dry to touch:	40 min.	-																		
Dry to assembly:	2 h	30 min.																		
Dry for sanding:	2 h	30 min.																		
Top coat:	2 h	30 min.																		
	Application with Airmix:	10% GRAVIHEL 1K THINNER Nozzle: 0,33 mm Pressure: 100 bar Flash-off between coats: 0 - 5 min. /20°C																		
	Brush application:	up to 5% GRAVIHEL 1K THINNER																		
	Shelf life:	2 years																		

FOR PROFESSIONAL USE ONLY - See Safety Data Sheet

The data may vary under various conditions.,

Any part of this information may change at any time without notice.

The information was derived from years of experience in the collaboration of Development and Technical Services and is the property of HELIOS Refinish.

We guarantee that the quality of work carried out according to our instructions delivers results while we disclaim any liability if any other products were used or if other factors influenced the final appearance.

The latest version of TDS supersedes all previous versions. You can obtain the latest version from general distributor in your country.